

## SIEVE ANALYSIS REPORT

**Customer:** Merinsac Tecnologias

**Product:** Galaxy Garnet 8-12


**Date:** Enero 18, 2018

**Lot #:** S/N

**Effective Size:** 1.52 mm

**Uniformity Coefficient:** 1.24

U.S. Mesh	Microns	% Retained	% Passing
6	3350	0.0	100.0
8	2360	4.0	96.0
10	2000	17.0	79.0
12	1700	52.0	27.0
14	1400	24.0	3.0
16	1180	3.0	0.0
18	1000	0.0	0.0
20	850	0.0	0.0
PAN		0.0	0.0



## SIEVE ANALYSIS REPORT

**Customer:** Merinsac Tecnologias

**Product:** Galaxy Garnet 30-40

**Date:** Enero 18, 2018

**Lot #:** S/N

**Effective Size:** 0.37 mm

**Uniformity Coefficient:** 1.29

U.S. Mesh	Microns	% Retained	% Passing
16	1180	0.0	100.0
18	1000	0.0	100.0
20	850	0.0	100.0
25	710	0.0	100.0
30	600	3.0	97.0
35	500	26.0	71.0
40	425	39.0	32.0
45	355	26.0	6.0
50	300	6.0	0.0
60	250	0.0	0.0
PAN		0.0	0.0

